

Product Information

Acrylonitrile Butadiene Styrene ABS200G30LU.BK

ABS200G30LU.BK is a cost effective, broad specification black compound based on utility ABS feedstocks and reinforced with 30% glass fiber. The addition of fiberglass increases tensile strength and rigidity, especially at elevated temperatures. **ABS200G30LU.BK** is lubricated for ease of mold release.

Although ABS resins in general exhibit an unusually broad latitude in processing conditions, **ABS200G30LU.BK** should be molded at the higher end of the typical melt temperature range, at between 500-520°F, and with mold surface temperatures of between 120-160°F, to promote best flow and surface appearance.

TYPICAL PROPERTIES

<u>PROPERTY</u>	<u>ASTM TEST METHOD</u>	<u>ENGLISH</u>		<u>S.I.</u>	
		<u>UNITS</u>	<u>VALUE</u>	<u>UNITS</u>	<u>VALUE</u>
Specific Gravity	D792	-	1.29	-	1.29
Water Absorption (24 hours immersion)	D570	%	0.2	%	0.2
Heat Deflection Temperature at 264 lbs/in ² (1.82 MPa)	D648	°F	210 min	°C	98 min
Mold Shrinkage Guideline*	1/8" section	%	0.1 to 0.3	%	0.1 to 0.3
Tensile Strength at Break	D638	lbs/in ²	13,000 min	MPa	90 min
Elongation at Break	D638	%	1-3	%	1-3
Flexural Strength	D790	lbs/in ²	16,000 min	MPa	110 min
Flexural Modulus	D790	lbs/in ²	900,000 min	MPa	6,207 min
Izod Impact Strength (Notched, 1/8" specimen)	D256	ft. lbs/in of notch	1.2 min	J/m	64 min
Rockwell Hardness	D785	M scale	M98	-	-

***Please review shrinkages projections for specific applications with an MDE Technical Representative.**

These mechanical property test data have been developed using injection molded specimens tested under standardized conditions; furthermore, many of the mechanical properties of thermoplastic materials can be influenced by changes in processing conditions, environmental factors such as temperature and humidity, and rate of application of stress. Therefore, these test results, which characterize typical production material, should not be used either to establish specification limits or alone as the basis for engineering design.

ABS200G30LU.BK

Processing Guidelines

Drying

Although ABS resins and compounds from MDE are shipped in moisture resistant packaging, in order to realize best surface appearance it is important that they are further dried before processing. The use of dehumidifying dryers is strongly recommended. The dew point of the drying air stream should be no more than 0°F, and preferably lower; the drying air temperature must be high enough to achieve a pellet temperature of about 180°F. If using a hopper drier, depending on air hose length and insulation of hoses and hopper, the drying air temperature may need to reach 200-210°F to achieve the required material temperature. Insulation of hoses and especially the hopper is strongly recommended. After the material temperature reaches 180°F, a residence time of 2 hours at this temperature is generally adequate to ensure that the material is ready to be processed. Note that dried material should be used within an hour, particularly in humid weather conditions; longer exposure times will usually result in a need to redry. If moisture analysis equipment is available, the acceptable maximum moisture content for ABS resins and compounds is 0.1%.

Temperature Guidelines

The following temperature guidelines are suggested for general use if a machine can be selected where shot size is 40-70% of nominal machine capacity.

<u>Tool Surface Temperature (°F)</u>	<u>Melt Temperatures (°F)</u>			<u>Typical Cylinder Temperatures (°F)</u>		
	<u>Max.</u>	<u>Preferred</u>	<u>Min.</u>	<u>Front</u>	<u>Center</u>	<u>Rear</u>
120-160	525	480-510	450	490	480	470

- Melt temperatures at the higher end of the range have been used successfully to help flow in very thin sections, provided cylinder residence times are short.
- A mold surface temperature in the suggested range improves surface appearance, helps consistency of mold fill and therefore consistency of dimensions, minimizes the effect of weld lines and also helps realize best molded part performance.
- A medium to fast injection speed maximizes weld line strength and minimizes molded in stress. Good venting of cavities is essential to allow faster fill without burning.

Screw Forward Time

Adequate screw forward time under follow-up pressure is especially important to ensure proper packing before gate freeze, during which time it is essential to maintain a "cushion" of about 1/8". Optimum screw forward time can be judged by a part weight vs. forward time plot. However, avoid overpacking, which by generating molded-in stresses can adversely affect part performance.

Screw Recovery

It is recommended that back pressures should be limited to 100-150 p.s.i. gauge to help ensure uniformity of the melt, yet minimize mechanical damage to the glass fibers and consequent loss of part performance. Screw rotation should also be as slow as possible consistent with cycle time goals, usually 40-80 r.p.m.

Mold Shrinkage

Standard ASTM test specimens are used to develop shrinkage guidelines. Test specimens are end-gated, 1/8 inch thickness, and molded at conditions recommended for this formulation. **Actual shrinkage in molded parts will depend on several variables including processing conditions, part configuration and gate location, both of which influence material flow direction, and wall section thickness.**