

Product Information

Nylon N60G14L, N60G14HL and N60G14HSL

N60G14L is a nylon 6 compound, reinforced with 15% glass fiber, which significantly improves strength and rigidity especially at elevated temperatures, while maintaining good toughness.

For molded parts, which are to be exposed to high temperatures for prolonged periods of time, the use of a heat stabilized compound is recommended. **N60G14HSL** incorporates a conventional stabilizer system, which offers excellent protection against thermal aging, but will tint the natural color, normally to a greenish hue.

For applications where preservation of natural color is important, including the accurate matching of colors, the use of **N60G14HL**, which contains an effective stabilizer system free from color effects, is suggested.

Each compound offers the high flow, easy processing and outstanding surface appearance characteristic of nylon 6 resins, and is lubricated for improved feed and mold release.

Reinforced nylon 6 compounds offer a unique combination of strength and rigidity, excellent static and dynamic fatigue resistance, natural lubricity, and resistance to the effects of broad range of chemicals, oils and solvents, and are therefore used for a very wide range of applications in every end-use category.

TYPICAL PROPERTIES DRY AS MOLDED

PROPERTY	ASTM TEST METHOD	ENGLISH		S.I.	
		UNITS	VALUE	UNITS	VALUE
Melting Range	D789	°F	420-435	°C	215-225
Specific Gravity	D792	-	1.23	-	1.23
Water Absorption (24 hours immersion)	D570	%	1.4	%	1.4
Heat Deflection Temperature at 264 lbs/in ² (1.82 MPa)	D648	°F	380	°C	193
Mold Shrinkage Guideline* (Flow Direction)	1/8" section	%	0.7	%	0.7
Tensile Strength at Break	D638	lbs/in ²	17,000	MPa	117
Elongation at Break	D638	%	4-6	%	4-6
Flexural Strength	D790	lbs/in ²	24,000	MPa	166
Flexural Modulus	D790	lbs/in ²	700,000	MPa	4,830
Izod Impact Strength (Notched, 1/8" specimen)	D256	ft. lbs/in of notch	1.2	J/m	64
Rockwell Hardness	D785	R scale	R121	-	-

***Please review shrinkage projections for specific applications with an MDE Technical Representative.**

All data generated using test specimens injection molded from natural color material. Inclusion of color pigments or other additives may change some or all of these test results. Test specimens are stored in a moisture proof container immediately after molding and contain less than 0.2% moisture; tests are conducted at 23°C and 50% relative humidity unless otherwise stated.

These mechanical property test data have been developed using injection molded specimens tested under standardized conditions; furthermore, many of the mechanical properties of thermoplastic materials can be influenced by changes in processing conditions, environmental factors such as temperature and humidity, and rate of application of stress. Therefore, these test results, which characterize typical production material, should not be used either to establish specification limits or alone as the basis for engineering design.

Nylon N60G14L, N60G14HL and N60G14HSL

Processing Guidelines

Drying

Nylon compounds from MDE are shipped in moisture resistant packaging, dried and ready to be processed. If drying is required after, for example, exposure of virgin resin to humid air for more than one hour, or for reground material, the use of dehumidifying dryers is strongly preferred.

The dew point of the drying air stream should be no more than -20°F , and preferably lower. The drying air temperature must be high enough to achieve a pellet temperature of $175\text{-}180^{\circ}\text{F}$. If using a hopper drier, depending on air hose length and insulation of hoses and hopper, the drying air temperature may need to reach $200\text{-}220^{\circ}\text{F}$ to achieve the required material temperature.

If the pellet temperature reaches 180°F , a residence time of 4 hours is generally adequate to ensure that the material is ready to be processed. Only if residence times are limited to 2 hours should a pellet temperature of 200°F be considered; at 200°F , there is a risk of material oxidation, with associated yellowing and loss of part performance.

Nylon compounds usually demonstrate visual evidence of unacceptably high moisture levels, such as uncontrollable nozzle drool, or splay or silver streaks on the molded part. Additional drying time is indicated if these characteristics are observed.

If moisture analysis equipment is available, an acceptable moisture content range for processing is 0.1% to 0.25% maximum.

Temperature Guidelines

The following temperature guidelines are suggested for general use if a machine can be selected where shot size is 40-70% of nominal machine capacity.

**Tool Surface
Temperature ($^{\circ}\text{F}$)**
150-200

Melt Temperatures ($^{\circ}\text{F}$)
Max. Preferred Min.
550 500-520 480

**Typical Cylinder
Temperatures ($^{\circ}\text{F}$)**
Front Center Rear
490 500 510

- A "reverse" temperature profile helps ensure a homogeneous melt, improves screw recovery and by accelerating the transition from solid pellets to a melt significantly reduces abrasive wear on screw and barrel surfaces.
- A mold surface temperature in the suggested range improves surface appearance, helps consistency of mold fill and therefore consistency of dimensions, minimizes the effect of weld lines and also helps realize best molded part performance.
- A fast injection speed maximizes weld line strength, minimizes molded in stress, and also contributes to achievement of best surface gloss. Good venting of cavities is essential to allow fast fill without burning.

Screw Forward Time

Adequate screw forward time under follow-up pressure is important to ensure proper packing before gate freeze, during which time it is essential to maintain a "cushion" of 1/8"-1/4". Optimum screw forward time can be judged by a part weight vs. forward time plot. Avoid overpacking, which can generate molded-in stresses.

Screw Recovery

It is recommended that low back pressures of 50 p.s.i. gauge be used to help development of an homogeneous melt, and ensure a consistent shot volume, while minimizing the risk of mechanical damage to the glass fibers with consequent loss of part performance. Screw rotation should also be as slow as possible consistent with cycle time goals, usually 40-80 r.p.m.

Mold Shrinkage

Standard ASTM test specimens are used to develop shrinkage guidelines. Test specimens are end-gated, 1/8 inch thickness, and molded at conditions recommended for this formulation. **Actual shrinkage in molded parts will depend on several variables including processing conditions, part configuration and gate location, both of which influence material flow direction, and wall section thickness.**