

Product Information

Nylon N12G30L and N12G30HSL

N12G30L is a nylon 12 compound, reinforced with 30% glass fiber. Nylon 12 resins and compounds exhibit substantially reduced moisture absorption compared with nylons 6 or 6.6, minimizing the effects of environmental humidity changes on mechanical and electrical properties, and significantly improving dimensional stability.

The addition of glass fiber further improves dimensional stability, and significantly increases rigidity, especially at high temperatures, while the practical toughness and ductility typical of nylon 12 is retained.

For applications which require resistance to the effects of extended exposure to high temperatures the use of **N12G30HSL**, which contains an effective heat stabilizer system, is recommended.

Nylon 12 resins and compounds exhibit excellent resistance to the effects of exposure to an even wider range of chemicals, solvents and oils than nylons 6 or 6.6, so are suitable for use in a wide range of aggressive environments.

Reinforced nylon 12 compounds offer an unusually broad processing latitude, and exhibit excellent molded part surface gloss.

TYPICAL PROPERTIES DRY AS MOLDED

<u>PROPERTY</u>	<u>ASTM TEST METHOD</u>	<u>ENGLISH</u>		<u>S.I.</u>	
		<u>UNITS</u>	<u>VALUE</u>	<u>UNITS</u>	<u>VALUE</u>
Melting Point	D789	°F	352	°C	178
Specific Gravity	D792	-	1.22	-	1.22
Water Absorption (24 hours immersion)	D570	%	0.45	%	0.45
Heat Deflection Temperature at 264 lbs/in ² (1.82 MPa)	D648	°F	320	°C	160
Mold Shrinkage Guideline* (Flow Direction)	1/8" section	%	0.1	%	0.1
Tensile Strength at Yield	D638	lbs/in ²	12,500	MPa	86
Elongation at Break	D638	%	6	%	6
Flexural Strength	D790	lbs/in ²	23,500	MPa	162
Flexural Modulus	D790	lbs/in ²	770,000	MPa	5,310
Izod Impact Strength (Notched, 1/8" specimen)	D256	ft. lbs/in of notch	4.5	J/m	240

***Please review shrinkages projections for specific applications with an MDE Technical Representative.**

All data generated using test specimens injection molded from natural color material. Inclusion of color pigments or other additives may change some or all of these test results. Test specimens are stored in a moisture proof container immediately after molding and contain less than 0.2% moisture; tests are conducted at 23°C and 50% relative humidity unless otherwise stated.

These mechanical property test data have been developed using injection molded specimens tested under standardized conditions; furthermore, many of the mechanical properties of thermoplastic materials can be influenced by changes in processing conditions, environmental factors such as temperature and humidity, and rate of application of stress. Therefore, these test results, which characterize typical production material, should not be used either to establish specification limits or alone as the basis for engineering design.

N12G30L and N12G30HSL

Processing Guidelines

Drying

Nylon compounds from MDE are shipped in moisture resistant packaging, dried and ready to be processed.

If drying is required after, for example, exposure of virgin resin to humid air for more than one hour, or for reground material, the use of dehumidifying dryers is strongly preferred.

The dew point of the drying air stream should be no more than -20°F , and preferably lower. The drying air temperature must be high enough to achieve a pellet temperature of $175\text{-}180^{\circ}\text{F}$. If using a hopper drier, depending on air hose length and insulation of hoses and hopper, the drying air temperature may need to reach $200\text{-}220^{\circ}\text{F}$ to achieve the required material temperature.

If the pellet temperature reaches 180°F , a residence time of 4 hours is generally adequate to ensure that the material is ready to be processed. Only if residence times are limited to 2 hours should a pellet temperature of 200°F be considered; at 200°F , there is a risk of material oxidation, with associated yellowing and loss of part performance.

Nylon compounds usually demonstrate visual evidence of unacceptably high moisture levels, such as uncontrollable nozzle drool, or splay or silver streaks on the molded part. Additional drying time is indicated if these characteristics are observed.

If moisture analysis equipment is available, an acceptable moisture content range for processing is 0.1% to 0.25% maximum.

Temperature Guidelines

The following temperature guidelines are suggested for general use **if a machine can be selected where shot size is 40-70% of nominal machine capacity.**

<u>Tool Surface Temperature ($^{\circ}\text{F}$)</u>	<u>Melt Temperatures ($^{\circ}\text{F}$)</u>			<u>Typical Cylinder Temperatures ($^{\circ}\text{F}$)</u>		
	<u>Max.</u>	<u>Preferred</u>	<u>Min.</u>	<u>Front</u>	<u>Center</u>	<u>Rear</u>
150-180	550	500-530	480	500	512	520

- A "reverse" temperature profile helps ensure a homogeneous melt, improves screw recovery and by accelerating the transition from solid pellets to a melt significantly reduces abrasive wear on screw and barrel surfaces.
- A mold surface temperature in the suggested range improves surface appearance, helps consistency of mold fill and therefore consistency of dimensions, minimizes the effect of weld lines and also helps realize best molded part Performance.
- A fast injection speed maximizes weld line strength and minimizes molded in stress, and also contributes to achievement of best surface gloss. Good venting of cavities is essential to allow fast fill without burning.

Screw Forward Time

Adequate screw forward time under follow-up pressure is important to ensure proper packing before gate freeze, during which time it is essential to maintain a "cushion" of $1/8\text{-}1/4\text{'}$. Optimum screw forward time can be judged by a part weight vs. forward time plot. Avoid overpacking, which generates molded in stresses.

Screw Recovery

It is recommended that back pressures of 50 p.s.i gauge to used to help development of a homogeneous melt, and to ensure consistent shot volume, while minimizing the risk of mechanical damage to the glass fibers with consequent loss of part performance. Screw rotation should also be as slow as possible consistent with cycle time goals, usually 40-80 r.p.m.

Mold Shrinkage

Standard ASTM test specimens are used to develop shrinkage guidelines. Test specimens are end-gated, $1/8$ inch thickness, and molded at conditions recommended for this formulation. **Actual shrinkage in molded parts will depend on several variables including processing conditions, part configuration and gate location, both of which influence material flow direction, and wall section thickness.**